


MATERIAL DATA SHEET

DESCRIPTION

CARAVAN / MOTORHOME OPENING WINDOW
SEAL LARGE BULB 25MM PANEL C/W WHITE
INSERT



ORDER CODE

CS 784W

| PARAMETER | VALUE |
|---------------------------------------|----------------------------|
| BASE MATERIAL | BLACK EPDM |
| HARDNESS | 65 – 75° SHORE A |
| TENSILE STRENGTH | 8.5MPA |
| ELONGATION @ BREAK | 285% |
| COMPRESSION SET (22 HOURS @ 70°C) | 20% |
| TEMPERATURE RANGE | -40°C TO +120°C |
| <u>AGED 70 HOURS @ 70°C</u> | |
| HARDNESS CHANGE | +1° SHORE A |
| TENSILE STRENGTH CHANGE | +4% |
| ELONGATION @ BREAK CHANGE | -9% |
| SPONGE MATERIAL | BLACK EXPANDED EPDM |
| DENSITY | 0.5 – 0.9G/CM ³ |
| WATER ABSORPTION | 2.5% |
| COMPRESSION SET 50% (22 HOURS @ 23°C) | 19% |
| COMPRESSION DEFLECTION (25%) | 80KPA |

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.

CS 784W CONTINUED

| | |
|--------------------------------------|--------------------|
| <u>HEAT RESISTANCE (168H @ 70°C)</u> | |
| COMPRESSION DEFLECTION CHANGE | -4% |
| INSERT MATERIAL | WHITE PVC |
| HARDNESS (ISO 868) | 90° SHORE A |
| DENSITY (ISO 868) | 1.52G/CM3 |
| TENSILE STRENGTH (UNE 21-117) | 14.2MPA |
| ELONGATION (UNE 21-177) | 250% |
| TEMPERATURE RANGE | -10°C TO +60°C |
| SEALANT | WHITE BUTYL MASTIC |
| SPECIFIC GRAVITY (ASTM D-71) | 1.3 |
| SOFTENING POINT (ASTM D-36) | 200°C |
| ELONGATION @ 25°C | 300% (MIN) |
| TEMPERATURE RANGE | -40°C TO +90°C |