

MATERIAL DATA SHEET

DESCRIPTION

**SEMI RIGID PVC FENDER WITH
FLEXIBLE INSERT – 30 METRE LENGTH**



ORDER CODE

PFSR 3284

PARAMETER	VALUE
MATERIAL - BASE	WHITE PVC
HARDNESS	84° SHORE A
TEMPERATURE RANGE	-20°C TO +60°C
TENSILE STRENGTH (BS2782 320A)	18.5MN/M ²
DENSITY (BS2782 620A)	1.27G/CC
ELONGATION @ BREAK (BS2782 320A)	325%
100% MODULUS (BS2782 320A)	11.9MN/M ²
COLD FLEX TEMPERATURE (BS2782 150B)	-7°C
BSS SOFTNESS NUMBER (BS2782 365A)	28
MATERIAL - INSERT	WHITE PVC
DENSITY (BS2782 620A)	1.24G/CM ³
HARDNESS	67° SHORE A
BSS SOFTNESS NUMBER (BS2782 365A)	58
TENSILE STRENGTH (BS2782 320A)	18.4MN/M ²
ELONGATION @ BREAK (BS2782 320A)	390%

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.

PFSR 3284 CONTINUED

PARAMETER	VALUE
100% MODULUS (BS2782 320A)	7.58MN/M ²
COLD FLEX TEMPERATURE (BS2782 150B)	-26°C