

## MATERIAL DATA SHEET

DESCRIPTION

JAGUAR MK2 TYPE BONNET REST SEAL



ORDER CODE

**SRS 1912**

PARAMETER	VALUE
SPONGE MATERIAL	EXPANDED EPDM SKINNED CLOSED CELL SPONGE
DENSITY RANGE	0.5 – 0.9 G/CM <sup>3</sup>
WATER ABSORPTION	5% MAX
COMPRESSION SET (22 HOURS @ R/T)	50%
COMPRESSION SET (24 HOURS RECOVERY)	25% MAX
OZONE RESISTANCE	EXCELLENT
WEATHER RESISTANCE	EXCELLENT
UV LIGHT RESISTANCE	EXCELLENT
MOULD GROWTH RESISTANCE	VERY GOOD
OIL RESISTANCE	NO
LOW TEMPERATURE FLEXIBILITY	PASS
OVEN AGEING (7 DAYS @ 70°C)	±30%

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.