

MATERIAL DATA SHEET

DESCRIPTION

AUTOMOTIVE OVER RIDER SECTION



ORDER CODE

AT 2010

PARAMETER	VALUE
MATERIAL	SATIN PVC
DENSITY (BS2782, 620A)	1.52G/CM ³
HARDNESS (BS2782, 365B)	78° SHORE A
BS SOFTNESS NUMBER (BS2782, 365A)	40
TENSILE STRENGTH (BS6469, 2.2)	13N/MM ²
ELONGATION @ BREAK (BS6469, 2.2)	270%
COLD FLEX (BS2782, 150B)	-20°C
COLD BEND (BS2782, 151A)	-30°C
RETENTION AFTER AGEING @ 80°C, 7 DAYS (BS6469, 2.3)	97%
VOLUME RESISTIVITY @ 23°C (BS2782, 230A)	6X10 ^Ω
VOLUME RESISTIVITY @ 70°C (BS2782, 230A)	6X10 ^Ω
LOSS OF MASS 80°C, 7 DAYS (BS6469, 4.1)	1.2MG/CM ²

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.