

## MATERIAL DATA SHEET

DESCRIPTION

**MORRIS MINOR 1000 CHROME FILLER STRIP**



ORDER CODE

**ATMM 1956**

PARAMETER	VALUE
SOLID MATERIAL	CLEAR PVC
HARDNESS (ISO 868)	90° SHORE A
DENSITY (ISO 868)	1.35 – 1.45G/CM <sup>3</sup>
TENSILE STRENGTH (UNE 21-117)	>11MPA
ELONGATION (UNE 21-177)	250 – 350%
TEMPERATURE RANGE	-10°C TO +60°C
<u>AGED 70 HOURS @ 70°C</u>	
HARDNESS CHANGE	+2° SHORE A
TENSILE STRENGTH CHANGE	+15%
COMPRESSION SET (ASTM D395)	40% (MAX)
OZONE RESISTANCE (70 HOURS @ 50°C, 50 PPHM, 20% EXT)	NO CRACKS
CHROME MATERIAL	ALUMINIUM FOIL
THICKNESS	50 MICRON
HARDENING	SOFT TEMPERED
COATING	LACQUERED

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.