


MATERIAL DATA SHEET

DESCRIPTION

**WHITE SOLID SILICONE RUBBER STRIP
25MM X 5MM**



ORDER CODE

SIL 3234

PARAMETER	VALUE
MATERIAL	SOLID SILICONE
DIMENSIONAL TOLERANCE – WIDTH – THICKNESS	±0.5MM ±0.55MM
HARDNESS (ASTM D2240, DIN ISO 7619-1)	55 – 65° SHORE A
TEMPERATURE RANGE	-60°C TO +230°C +250°C INTERMITTENT
TENSILE STRENGTH (ISO 37 TYPE 1, ASTM D412 DIE C, DIN 53504 TYPE S1)	7MPA (MIN)
COMPRESSION SET 24 HOURS @ 150°C (BS903 PT A6 TYPE B, DIN/ISO 815 TYPE B)	13% (TYP)
ELONGATION @ BREAK (ISO 37 TYPE 1, ASTM D412 DIE C, DIN 53504 TYPE S1)	280% (MIN)
TEAR STRENGTH (ASTM D264 DIE B)	12.5N/MM (MIN)
ABRASION RESISTANCE	110MM ³
FLAMMABILITY – FAR 25/JAR 25/CS 25 APPENDIX F, PART 1, (A)(1)(IV) AND (A)(1)(V) HORIZONTAL	PASS
AUTOMOTIVE STANDARD PART 571FMVSS302	PASS
FDA APPROVAL (21CFR177.2600)	PASS

GENERAL CHARACTERISTICS

EXCELLENT RESISTANCE TO OZONE, OXIDATION, ULTRAVIOLET LIGHT,

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.

SIL 3234 CONTINUED

PARAMETER	VALUE
CORONA DISCHARGE, COSMIC RADIATION, IONISING RADIATION AND WEATHERING IN GENERAL	