

## MATERIAL DATA SHEET

DESCRIPTION

**BLACK DUAL HARDNESS BULB SEAL  
WITH SELF ADHESIVE BASE**



ORDER CODE

**SRS 3292**

PARAMETER	VALUE
BASE MATERIAL	BLACK EPDM
HARDNESS	65 – 75° SHORE A
TENSILE STRENGTH	11MPA
ELONGATION @ BREAK	500%
TEAR STRENGTH	50KN/M
COMPRESSION SET (22 HOURS @ 70°C)	21%
OZONE RESISTANCE (72 HOURS @ 40°C, 25 PPHM, 20% EXT)	NO CRACKS
TEMPERATURE RANGE	-40°C TO +120°C
<u>AGED 70 HOURS @ 70°C</u>	
HARDNESS CHANGE	0° SHORE A
TENSILE STRENGTH CHANGE	+9%
ELONGATION @ BREAK CHANGE	0%
SPONGE MATERIAL	BLACK SKINNED EXPANDED EPDM
DENSITY RANGE	0.5 – 0.9G/CM <sup>3</sup>

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.

**SRS 3292 CONTINUED**

WATER ABSORPTION	5% (MAX)
COMPRESSION SET (22 HOURS @ R/T)	50%
OZONE RESISTANCE	EXCELLENT
WEATHER RESISTANCE	EXCELLENT
UV LIGHT RESISTANCE	EXCELLENT
MOULD GROWTH RESISTANCE	VERY GOOD
OIL RESISTANCE	NO
LOW TEMPERATURE FLEXIBILITY (-40°C)	PASS
OVEN AGEING (7 DAYS @ 70°C)	±30%
ADHESIVE TAPE	3M ACRYLIC FOAM
TAPE THICKNESS WITHOUT LINER	0.8MM ± 0.1MM
COLOUR	GREY
DENSITY	650 ± 100KG/M <sup>3</sup>
ADHESIVE TO EPDM	E2 HEAT ACTIVATED
ADHESIVE LINER SIDE	AR7 ACRYLATE
T-PEEL TO RUBBER (24 HOURS @ R/T)	18N/CM
SHELF LIFE (STORED @ 20°C 50% HUMIDITY)	12 MONTHS