

MATERIAL DATA SHEET

DESCRIPTION

**WHITE TIMBER BUBBLE SEAL
Ø6 BUBBLE X 50M COIL**



ORDER CODE

TFS 3299

| PARAMETER | VALUE |
|-----------------------------------|-----------------------|
| MATERIAL – BUBBLE AND BARBS | SILPLEX (TPE) |
| RELATIVE DENSITY | 1.13G/CM ³ |
| SHORE HARDNESS | 43° SHORE A |
| TENSILE STRENGTH | 6.6MPA |
| TEAR STRENGTH | 23N/MM |
| COMPRESSION SET (22 HOURS @ 70°C) | 34% |
| WEAR RESISTANCE | 320MM ³ |
| ELONGATION @ BREAK | 520% |
| MATERIAL – RIGID SPINE | POLYPROPYLENE |
| RELATIVE DENSITY | 0.91G/CM ³ |
| VICAT SOFTENING POINT (B) | 154°C |
| HEAT DEFLECTION TEMPERATURE | 91°C |
| CHARPY NOTCHED IMPACT STRENGTH | 50KJ/M ² |
| TENSILE STRENGTH | 27MPA |
| FLEXURAL MODULUS (23°C) | 1300MPA |

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.

| PARAMETER | VALUE |
|---|-------------------------------------|
| COEFFICIENT OF THERMAL EXPANSION | $6 \times 10^{-5} / ^\circ\text{C}$ |
| THERMAL CONDUCTIVITY @ 23°C | 0.16W/M.K |
| ELONGATION AT BREAK | 20 – 40% |
| <u>GENERAL CHARACTERISITICS</u> | |
| <ul style="list-style-type: none">• RESISTANT TO MOST PAINTS AND VARNISHES• UV & OZONE STABLE• GOOD ACOUSTIC PROPERTIES• HIGH PERFORMANCE OVER EXTREME TEMPERATURES• SUPERIOR AGEING PROPERTIES• EXCELLENT DEFLECTION RECOVERY | |