

MATERIAL DATA SHEET

DESCRIPTION

**WHITE TIMBER BUBBLE SEAL
Ø8 BUBBLE X 50M COIL**



ORDER CODE

TFS 3302

PARAMETER	VALUE
MATERIAL – BUBBLE AND BARBS	SILPLEX (TPE)
RELATIVE DENSITY	1.13G/CM ³
SHORE HARDNESS	43° SHORE A
TENSILE STRENGTH	6.6MPA
TEAR STRENGTH	23N/MM
COMPRESSION SET (22 HOURS @ 70°C)	34%
WEAR RESISTANCE	320MM ³
ELONGATION @ BREAK	520%
MATERIAL – RIGID SPINE	POLYPROPYLENE
RELATIVE DENSITY	0.91G/CM ³
VICAT SOFTENING POINT (B)	154°C
HEAT DEFLECTION TEMPERATURE	91°C
CHARPY NOTCHED IMPACT STRENGTH	50KJ/M ²
TENSILE STRENGTH	27MPA
FLEXURAL MODULUS (23°C)	1300MPA

This information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check its validity and to test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.

TFS 3302 CONTINUED

PARAMETER	VALUE
COEFFICIENT OF THERMAL EXPANSION	$6 \times 10^{-5} / ^\circ\text{C}$
THERMAL CONDUCTIVITY @ 23°C	0.16W/M.K
ELONGATION AT BREAK	20 – 40%
<u>GENERAL CHARACTERISITICS</u>	
<ul style="list-style-type: none">• RESISTANT TO MOST PAINTS AND VARNISHES• UV & OZONE STABLE• GOOD ACOUSTIC PROPERTIES• HIGH PERFORMANCE OVER EXTREME TEMPERATURES• SUPERIOR AGEING PROPERTIES• EXCELLENT DEFLECTION RECOVERY	